



INTRODUCTION

Si-COAT® 570hs™ High Voltage Insulator Coating (HVIC) [high solids] is a room temperature vulcanizing (RTV) silicone product that contains less solvent than regular **Si-COAT® 570™** HVIC. Unlike competitive products, it is supplied ready-to-use without the need of additional thinning or excessive mixing/shaking before use. **Si-COAT® 570hs™** HVIC is based on extensive research and development work that led to the award of a patent. The basis of the **Si-COAT® 570hs™** patent is the optimally-sized alumina trihydrate (ATH) particle and the optimum concentration of the ATH ingredient, discovered by the engineers and chemists at CSL Silicones Inc. The presence of ATH in the formulation of the HVIC is necessary to protect the coating from the damaging effects of tracking under high electrical activity along the surface of the coating. It is essential that the ATH particle be optimally-sized and in an optimum concentration in order to promote long-term hydrophobicity of the coating.

The downside to the presence of ATH is the potential for the filler to settle during storage and transportation. In order to alleviate the problem, competitive coatings rely on a very fine particle size ATH (below 1 micron diameter). However, this fine particle size is far from the optimum size (13 microns) patented by CSL. By virtue of other key ingredients and a unique manufacturing process, the engineers and chemists behind **Si-COAT® 570hs™** have achieved a finished product in which the larger ATH particle will minimize settling. Hence, excessive agitation prior to application is also minimized, making **Si-COAT® 570hs™** one of the easiest HVICs to use.

Apart from its very long life and ease-of-use qualities, **Si-COAT® 570hs™** was the first to introduce the benefit of strong adhesion to the insulator surface. It is ideally suited for unprimed application to glass, porcelain and polymer (silicone and EPDM) insulators under all voltage conditions from distribution to very high voltage. Over its greater than 15 years of service history, **Si-COAT® 570hs™** has distinguished itself from its competition by virtue of flawless performance without a single failure of any type. That is far more than any competitor can claim of their HVIC.

For ultimate suppression of leakage current and an untarnished service life greater than that of any other HVIC, turn to **Si-COAT® 570hs™** by CSL Silicones Inc.

PRODUCT DESCRIPTION

A single component, RTV, moisture cure, high-build polysiloxane coating providing excellent long-term hydrophobicity, hydrophobicity recovery, electrical characteristics and UV tolerance leading to suppression of leakage current, reduction of pollution related flashover risk and a long service life.

INTENDED USES

Suitable for use on both new insulators and old insulators to be refurbished. Can be used, unprimed, on a variety of insulator substrates including glass, porcelain, HTV silicone, LSR type silicone and EPDM.

Further suitable as a refresh coating over old silicone HVICs provided the old HVIC is properly cleaned and still displays strong adhesion to the insulator surface.

Can be used in a variety of pollution environments including, but not limited to, salt spray, salt fog, industrial (cement dust, fly ash, carbon black, acid emissions, etc.) and desert sand.

Designed for use in AC and DC systems, in substations of all voltage levels and on transmission lines under all voltage conditions ranging from low distribution voltages to very high transmission voltages.

May also be used on metal substrates to act as a high dielectric strength insulating coating with excellent adhesion and long service life, as is typically required in railway and other high voltage applications.

PRODUCT CHARACTERISTICS AND PRACTICAL INFORMATION

Color	Clay Gray or White. Custom colors may be available dependent on formulation requirements
Gloss Level	Semi-gloss
Percent Solids	75% by volume, nominal 84% by weight, nominal
Theoretical Thickness	15.0 mil ± 4 mil (380 ± 100 microns) dry film thickness (DFT) 20.0 ± 5 mil (500 ± 130 microns) wet film thickness (WFT)

Theoretical Coverage	15.0 mils (380 µ) DFT
sq. ft per US gal.	80,4
sq. ft per lb	7,6

sq. m per liter	2,0
sq. m per kg	1,6

Allow appropriate loss factor:

Practical Coverage = Theoretical Coverage x [100% - Loss%].

Practical Application Thickness Guidance:

380 microns ± 100 microns, in accordance with IEEE Std 1523TM-2002 (IEEE Guide for the Application, Maintenance, and Evaluation of Room Temperature Vulcanizing (RTV) Silicone Rubber Coatings for Outdoor Ceramic Insulators)

Method of Application: Airless spray, brush or dip

Application Temperature Range:

41 to 140°F (5 to 60°C) [ambient]
41 to 266°F (5 to 130°C) [substrate]

DRYING TIME:

Skin-over Time	20-25 minutes nominal*
Tack-free Time	30-40 minutes nominal*
Cure Through	6 hours nominal*
Full Physical Characteristics	7 days nominal*

*At standard conditions [77°F (25°C) and 50% relative humidity – 10 mils wet film thickness]


REGULATORY DATA

Flash Point	100°F (38°C)
VOC	1.7 lb/US gallon (200 g/liter), nominal
Product Weight	10.6 lb/US gallon (1.27 kg/liter), nominal

PHYSICAL PROPERTIES

(Typical properties - values not to be used as specifications)

Uncured	
Appearance	Thick Paint
Viscosity	2500 to 4000 cP
Cure System	Neutral, moisture cure
Cured At Standard Conditions* for 7 Days	
Dielectric Strength (ASTM D149)	718.3 V/mil @ 21.3 mil (282.8 kV/cm @ 0.054 cm)
Volume Resistivity (ASTM D257)	>2.35 x 10 ¹² Ω.in (5.96 x 10 ¹⁶ Ω.cm)
Surface Resistivity (ASTM D257)	1.26 x 10 ¹⁶ Ω/□
Dissipation Factor (ASTM D150)	at 100 Hz: 0,0234 at 100 kHz: 0,00586
Dielectric Constant (ASTM D150)	at 100 Hz: 3.13 at 100 kHz: 3.05



Tracking Wheel Withstand (CEA LWIWG-01)	>1,000 hrs
Dry Arc Resistance (ASTM D495)	Track: 186 sec. Burnout: > 450 seg.
Temperature Stability	-40 a 480°F (-40 a 250°C)
Thermal Expansion Coefficient	1.33 x 10 ⁻⁵ in/in.°F (2.4 x 10 ⁻⁵ cm/cm.°C)
Thermal Conductivity	1.70 x 10 ⁻⁵ BTU/hr.ft °F (7.0 x 10 ⁻⁴ Cal/sec.cm.°C)
Loss Tangent at 100 Hz (ASTM D150)	0.0234
Water Repellency Angle (IEC 62073)	Static: 116.0 degrees Advancing: 114.0 degrees Receding: 92.0 degrees
UV & Salt Fog Accelerated Weathering (IEC61109, 5,000 hours)	No degradation
Inclined Plane Tracking & Erosion Test (IEC 60587)	PASS: 1A 4.5; 1B 4.5
Adhesion Testing (IEEE 957)	Water Blast Test: PASS
Adhesion Testing (CEA LWIWG-02)	100 hrs Boiling Water Test: PASS

*At standard conditions 77°F (25°C) and 50% relative humidity.

SURFACE PREPARATION & CLEANLINESS

All surfaces to be coated should be free of dirt, dust, grease, oil, release agents, curing compounds, and other foreign matter including frost, water and microscopic condensed moisture. In addition, prior to applying the coating, all surfaces must be dry. Such precaution will ensure proper adhesion of the **Si-COAT® 570hs™** coating to the insulator surface.

High-pressure water washing is the suggested method for cleaning the insulator surface. The suggested pressure washing parameters are 3,000 psi @ 8 – 10 gallons per minute (210 kg/cm² @ 30 – 40 liters per minute). Insulators contaminated with cementitious material should be cleaned with a dry abrasive cleaner such as crushed corncob or walnut shells mixed with limestone.

For insulators covered in silicone or hydrocarbon grease, remove the bulk of the grease with a dry abrasive cleaner as above, or by hand wiping with a rag. Once the bulk of the grease has been removed, the surface should be wiped clean using an oil-free solvent such as acetone. Isopropyl alcohol is suggested for the final wipe and coating should commence once the insulators are dry.

If for whatever reason the **Si-COAT® 570hs™** application is delayed after cleaning of the insulator, the insulator must be re-cleaned.

COATING APPLICATION

Mixing: **Si-COAT® 570hs™** is supplied as a one-part, ready-to-use coating. It is normal, however, during shipment or extended storage, for carrier solvent to rise to the top of the container. Upon opening of the container, mix by power agitator until an even consistency of coating is obtained.

Application: All surfaces should be clean and dry prior to application. The coating should be applied in a manner that prevents runs, sags, drips, spills, etc. and that completely covers surfaces without holidays. The temperature of the surface to be coated should be between 41 and 122°F (5 and 50°C) and environmental temperature should be at least 5°F (3°C) above the dew point prior to and during application.

All areas particularly prone to corrosion such as the caps and pins of insulator discs can also be coated to provide added protection and a uniform monolithic surface.

The insulator should be coated with a minimum 10.0 mils (254 microns) DFT of **Si-COAT® 570hs™**. The average DFT of **Si-COAT® 570hs™** is 15 mils (380 microns) and the maximum advisable DFT is 50 mils (1,270 microns).

Airless Spray: Recommended - Tip sizes to range from 17 to 21 thou (432 to 533 micron) with a 6 to 10 inch (15 to 25 cm) fan at 1 ft (30 cm) distance. Pump pressure ratio of 40:1. Total output fluid pressure at spray tip not less than 2,000 psi (141 kg/cm²). Minimum 1/2 inch (1.3 cm) ID, maximum 50 ft (15 m) length spray line. See recommended spray apparatus in Section 9.

Dip: Suitable - Constant nitrogen purge should be used over liquid surface in container to avoid formation of skins while dipping. Rotate insulators after dipping to avoid formation of drip marks. Generally, higher DFT is achieved. Thinning may be necessary.

Brush: Suitable - Generally, 10 to 15 mil (254 to 381 micron) DFT can be achieved.

Thinner: Naphtha or Odorless Mineral Spirits. It is recommended, however, that **Si-COAT® 570hs™** be used at the viscosity supplied. If product is thinned, do not exceed local environmental legislation.

Cleaner: Naphtha or Odorless Mineral Spirits.

Work Stoppages & Restarts: Work stoppages are not recommended with only partial consumption of a container of **Si-COAT® 570hs™**. If work must stop after only a portion of a container of **Si-COAT® 570hs™** is used, seal to minimize air and moisture contact with the coating by covering the surface of the coating with a sheet of polyethylene film, then reseal the container to be airtight.

Upon reopening the container to restart work, peel back the polyethylene film. If curing of the coating has occurred, use a utility knife to cut the cured coating away from the wall of the container. Peel away the cured layer of coating to expose fresh coating underneath.

Clean-up: Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with the following cleaner.

Fully cured coating is environmentally benign (will not harm) and is suitable for landfill disposal. However, always check local environmental regulations before disposal.

RECOMMENDED SPRAY APPARATUS

Part Description	Graco Part No.
2 gallon ASME 100% stainless steel pressure tank with air-powered agitator	236-156
Gun/air dual regulation kit	235-042
Fluid outlet strainer	240-418
HVLP (High Volume, Low Pressure) spray gun complete with 0.042 in. (1.067 mm) fluid nozzle	239-560
Air spray gun complete with 0.110 in. (2.794 mm) fluid nozzle	239-545
Fluid hose assembly, nylon tube, neoprene cover 25 ft. (7.6 m) length, 3/8 in. (9.5 mm) ID	205-142
Air hose assembly, BUNA-N tube, neoprene cover 25 ft. (7.6 m) length, 5/16 in. (7.9 mm) ID	210-867
Polyethylene tank liner (20 per case)	112-632
Air line desiccant dryer	106-493
Air line filter	106-149
Air line filter	239-601
Repair kit for HVLP gun needle/nozzle	239-595
Graco gun repair kits for spray guns	237-398
Tips for airless spray gun ('xxx' refers to the last three part numbers of Graco tips)	286-xxx

PRODUCT CHARACTERISTICS

Level of sheen and surface finish is dependent on application method. Avoid using a combination of application methods whenever possible. Best results in terms of gloss and appearance will always be obtained with airless spray.

If over coating **Si-COAT® 570hs™** after weathering or ageing, ensure the coating is fully cleaned to remove all surface contamination such as dust, grease, oil, salt crystals, traffic fumes, etc. before application of a further coat of **Si-COAT® 570hs™**.

This product must only be thinned using the recommended thinners. The use of alternate thinners may inhibit the curing mechanism of the coating.

Do not apply to substrate temperatures below 41°F (5°C).

When applying **Si-COAT® 570hs™** in confined spaces ensure adequate ventilation and/or respiratory equipment is available. Consult the **Si-COAT® 570hs™** SDS for further details.

Condensation occurring during or immediately following application may result in a matte finish.

Si-COAT® 570hs™ has excellent tolerance to airborne chemical exposure. When severe chemical or solvent splashing/pooling is likely to occur, please contact CSL Silicones Inc. for information regarding suitability.

SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given in this document, the **Si-COAT® 570hs™** Safety Data



Sheet (SDS) and the container(s), and should not be used without reference to the SDS that CSL Silicones Inc. has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards & regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes may be emitted that will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult CSL Silicones Inc. for further advice.

PACKAGING*

Size (unit)	Product Volume	Net Weight	Shipping Weight
1 US gal	1.0 US gal (3.8 L)	10.6 lb (4.8 kg)	12.1 lb (5.5 kg)
2.5 US gal	2.5 US gal (9.5 L)	26.6 lb (12.1 kg)	29.5 lb (13.4 kg)
5 US gal	5.0 US gal (18.9 L)	52.9 lb (24.0 kg)	57.3 lb (26.0 kg)
50 US gal	50.0 US gal (189.3 L)	530.0 lb (240.0 kg)	574.3 lb (260.5 kg)

*For availability of other package sizes, please contact CSL Silicones Inc.

STORAGE

Shelf Life: 12 months from date of manufacture in the original unopened container below 90°F (32°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat or ignition.

If your country or region experience high temperatures, CSL strongly recommends storing the coating material in an air-conditioned dry area, away from sources of heat or ignition, preferably below 73°F (23°C).

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this document without first obtaining written confirmation from CSL Silicones Inc. as to the suitability of the product for the intended purpose does so at his/her own risk. The information contained herein has been prepared in good faith to comply with applicable federal and provincial (state) law(s). However, no warranty of any kind is given or implied and CSL Silicones Inc. will not be responsible for any damages, losses or injuries that may result from the use of any information contained herein. While CSL endeavors to ensure all advice it gives about the product (whether in this document or otherwise) is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless CSL specifically agrees in writing to do so, it does not accept any liability whatsoever or howsoever arising for the performance of the product, or for any consequential loss or damage arising out of the use of the product. Any warranty, if given or specific Terms & Conditions of Sale are contained in CSL's Terms & Conditions of Sale, a copy of which can be obtained upon request. The information contained herein is liable to modification from time-to-time in light of experience and CSL's policy of continuous product improvement. It is the user's responsibility to check that this document is current prior to using the product. This document must not be used for specification writing.

CSL Silicones Inc.
144 Woodlawn Rd. W.
Guelph, ON N1H 1B5
Canada

T +1 519.836.9044
TF + 1 800.265.2753
cslsilicones.com

SI-COAT® 570hs™ Reviewed 2023-11-27
Internal Use | Publication CSL570HSP23.11
All trademarks registered. All rights reserved.

